




Kingspan XPS TS250

Technical Data Sheet

Insulation Boards for Inverted Roofs, Basements, Car Park Decks



- Rigid extruded polystyrene insulation with thermal conductivity as low as $0.039\text{W}/(\text{m}\cdot\text{K})$ at 23°C mean temperature (ASTM C518-21)
- Protects waterproofing membrane
- With compressive stress exceeding 250kPa at 10% deformation (ASTM D1621-20)
- Compatible with green roof systems
- Easy to handle and install
- Ideal for new build and refurbishment
- Manufactured with a CO_2 blowing agent that has zero ODP low GWP

Product Information

Product Description

Kingspan Hao Wei XPS TS250 is a pink coloured rigid extruded polystyrene insulation board. The core is manufactured with a CO₂ blowing agent.

This product is made in Malaysia.

General

Cutting

- Cutting should be carried out either by using a fine toothed saw, a hot wire system or by scoring with a sharp knife and snapping the board over a straight edge.
- Ensure accurate trimming to achieve close-butting joints and continuity of insulation.

Packaging and Storage

- The packaging of Kingspan Insulation products should not be considered adequate for outdoor protection.
- Ideally, boards should be stored inside a building.

If, however, outside storage cannot be avoided, then the boards should be stacked clear of the ground and covered with an opaque polythene sheet or weatherproof tarpaulin.

Boards should not be left in the sun covered by either a transparent or a dark plastic sheet, since in both cases, board temperatures can build up to a level hot enough to appreciably alter board dimensions or cause warping.

Standards and Approvals

Kingspan Hao Wei XPS TS250 is manufactured under a management system certified to ISO 9001:2015.

Technical Specifications

Property	Value	Test Standard
Product Dimension (L x W) (mm)	1200 x 600 (For other dimensions, please consult the technical department.)	-
Product Thickness (mm)	50	-
Edge Profile	Square Edge (Shiplap also available)	-
Thermal Conductivity at 23°C (W/(m.K))	≤ 0.039	ASTM C518-21
Compressive Stress at 10% Deformation (kPa)	≥ 250	ASTM D1621-16
Minimum Density (kg/m ³)	29	ASTM D1622-20

Contact Details

Asia Region

Kingspan Insulation Pte Ltd

1 Commonwealth Lane | #07-26/27 | Singapore 149544

T: (+65) 6653 2934

E: info@kingspaninsulation.asia

<https://www.kingspan.com/sg/en/business-groups/kingspan-insulation/>

© Kingspan and the Lion Device are Registered Trademarks of the Kingspan Group plc in Singapore, Malaysia, Vietnam, Thailand, the Philippines, and other countries. All rights reserved.

No rights can be derived from this document. Changes, typesetting and printing errors reserved.
This version replaces all previous versions.

Kingspan Insulation Pte Ltd reserves the right to amend product specifications without prior notice. The information, technical details and fixing instructions etc. included in this literature are given in good faith and apply to uses described. Recommendations for use should be verified as to the suitability and compliance with actual requirements, specifications and any applicable laws and regulations. For other applications or conditions of use, Kingspan Insulation offers a Technical Advisory Service the advice of which should be sought for uses of Kingspan Insulation products that are not specifically described herein.

To ensure you are viewing the most recent and accurate product information, please contact us

